

HAC8240

HAC8240 is high impact PC/ABS resin.HAC8240 has an excellent impact properties.HAC8240 is mainly used in road signal, panel parts, optical parts, large thin-wall product, etc.

Properties	Standard	Unit	Condition	Typical Value
Physical				
Density	ASTM D792	g/cm ³		1.1
Melt Index	ASTM D1238	g/10min	230℃×10kg	20
Mold Shrinkage	ASTM D955	%		0.5~0.7
Mechanical				
Tensile Strength	ASTM D638	MPa		52
Tensile Elongation at Break	ASTM D638	%		80
Flexural Strength	ASTM D790	MPa		65
Flexural Modulus	ASTM D790	MPa		2100
Notched Izod Impact,3.2mm	ASTM D256	J/m	3.2mm,Notched	700
Thermal				
Heat Deflection Temp. 1.82MPa Unannealed	ASTM D648	℃	1.82MPa	95
VICAT	ASTM D1525	℃	B	114
Flammability				
Flammability	UL-94	Class	1.6mm	HB
Electrical Properties				
Volume Resistivity	IEC 60093	Ohm-cm	/	> 1.0E+15
Surface Resistivity	IEC 60093	Ohm	/	> 1.0E+15

Note: 1) These are typical property values, not specifications.

2) In case of colored products, the values could vary slightly by color.

3) Values are measured at 23℃ and in RH of 50% on injection molded specimens.

4) UL File No. E65424 (CSA File No. LS 66457)、E254819

Disclaimer:

"To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the data compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or process described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. You may not copy this document to a Web site.

Kumho-Sunny expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication."

For more information please click:www.kumhosunny.com

HAC8240

Processing Parameters	Typical Value	Unit
Drying Temperature	90~100	℃
Drying Time	4~6	hour
Maximum moisture content		%
Barrel Temperature		
Rear		℃
Middle		℃
Front		℃
Nozzle		℃
Melt Temperature	220~260	℃
Mold Temperature	50~80	℃
Back Pressure		MPa
Screw Speed		rpm

Note:

1)The above data is only for reference. Exact settings have to follow the product,injection machine and mold.

Disclaimer:

To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the data compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or process described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. You may not copy this document to a Web site.

Kumho-Sunny expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no endorsement of any product or process, and we expressly disclaim any contrary implication.

For more information please click:www.kumhosunny.com